



## General description

NM Laminating 160 is designed to be used when there are high demands of yellowing-resistance.

Laminating can take place at room temperature.

Full cure at:

+175°C after approx. 4 minutes.

+150°C after approx. 10 minutes.

+130°C after approx. 15 minutes.

## Typical applications:

- Producing of epoxy laminates with demands of high yellowing resistance.

## Typical properties

### **Resin:**

NM Laminering 160

### **Hardener:**

NM Härdare 2962

### **Mixing ratio:**

Resin-Hardener 100-25 by weight

*Density:* 1131 kg/m<sup>3</sup>

*Viscosity at 25°C:* 400 mPa·s

*Potlife 100g 20°C:* ~ 1 hour

*Tensile strength:* 52 MPa

*Elongation to break:* 2%

*Tg at 4 minutes 175°C:* 100°C

*Colour:* Transparent

### **Normal packing:**

*Resin:* 4.0 kg

*Hardener:* 2 x 0.5 kg

*Cleaning solvent:* Acetone

## NILS MALMGREN AB

P.O.Box 2039  
S-442 02 YTTERBY

Phone: +46 303-936 10  
Fax: +46 303-928 55

E-mail: [info@nilsmalmgren.se](mailto:info@nilsmalmgren.se)  
Web: [www.nilsmalmgren.se](http://www.nilsmalmgren.se)

