



# NM Flexible Putty 705 Flex

NM Flexible Putty 705 Flex is an elastic two-part solventfree epoxy resin with a considerable lower viscosity than NM Flexible Putty 705.

This will make spreading easier on large areas.

## Typical applications

- Elastic layer in NM Tank system.

## Typical properties

**Resin:**

NM Spackel Elastic 705

**Hardener:**

NM Härdare 701

**Mixing ratio:**

Resin-Hardener 100-23 by weight

<i>Density:</i>	1347 kg/m <sup>3</sup>
<i>Viscosity at 25°C:</i>	Tixotropic
<i>Potlife 100g 20°C:</i>	30 minutes
<i>Flexibility at +20°C:</i>	more than 50 %
<i>(properties of material)</i>	
<i>Flexibility at -20°C:</i>	more than 30 %
<i>(properties of material)</i>	
<i>Hardness Shore A:</i>	70
<i>Minimum curing temp:</i>	+ 5°C
<i>Chemical resistance:</i>	see table
<i>Colour:</i>	Greyish white
<i>Normal packing:</i>	8.7 + 2.0=10.7 kg
<i>Cleaning solvent:</i>	Acetone